



HC-5619

Optically Clear UV-curable Hard Coat

Features

- Anti-fingerprint, anti-scratch and anti-fog
- High Tg
- Excellent steel wool scratch resistance
- Fast UV-curable
- High hardness

Description

- UV-curable hard coat

Properties of cured HC-5619 on plastic

Test parameters	HC-5619
<u>Process</u>	
Solid content (%)	30
Solvent use and %	MIBK, 70
Viscosity of 30% solution (cps, 25°C)	6
<u>Film properties</u>	
% Transmission	93
% Haze	0.1
Pencil Hardness on PET	5 H
5H pencil with weight	600 gram
Adhesion	100/100
% T after steel wool (SW) test SW conditions = 100 g/cm ² /100 time	92
Delta Haze after SW	0.1
Surface energy mN/m ²	23
<u>Solvent resistance properties</u>	
Ethanol soak, 24 hrs (adhesion, appearance)	100/100*, O**
IPA soak, 24 hrs (adhesion, appearance)	100/100, O
Ethanol at 60 °C soak, 24 hrs (adhesion, appearance)	100/100, O
Adhesion after moisture (40 °C, 95% RH, 24 hrs)	100/100, O
QUV (72 hrs) - yellowing check	O
QUV + Ethanol soak x 72 hrs - adhesion check	100/100, O

*100/100 = no delamination of the x-hatch test

**O = no delamination, no haze, no pocket and is excellent appearance

APPLICATIONS

UV-curable hard coat for plastic film

TYPICAL PROPERTIES of NEAT RESIN

Liquid

Viscosity (cps, 25 °C)	5,000 to 6,000
Storage (°C)	20 - 25
Shelf life (15 - 25 °C)	3 months
Pot life (15 - 25 °C)	2 months

Cured film

Shrinkage (volume, %)	6
Hardness – Shore D	95
Glass transition temperature (DMA, °C)	115

Refractive index of cured film (25°C) @ 589 nm	1.51
---	------

Physical properties tested at 25°C, 50% RH (ASTM D638)

Tensile strength, MPa	20
Elongation (%)	5
Modulus, MPa	1,500

TYPICAL PROPERTIES of COATED FILM

Viscosity (cps, 25 °C in 50% PM) 6-8
Suggested solvent: Methyl Isobutyl Ketone (MIBK), Methyl Ethyl Ketone (MEK), propylene glycol monomethyl ether (PM or PGME), IPA, Ethyl Acetate or mixture of solvents

Suggested hard coat solution for process: 25 – 50 wt % of neat HC-5619 in Methyl Isobutyl Ketone (MIBK) or 1:3 ratio of IPA and Ethyl Acetate.

Process

Film:	Plastic films (treated plastic film will enhance adhesion)
Coating:	Wire bar, roller coat, knife coat, dip coat or spin coat
Pre-curing:	60 – 80 °C for 1 – 2 min, IR heating is acceptable
UV-curing:	High, medium pressure Mercury lamp or Fusion lamp
	UV dose: 500 – 600 mJ/cm ²

Properties of coated film (3-5 µm)

<u>Pencil Hardness</u>	
TAC film (10-15 µm)	4H – 5H
PET film	5H – 6H
PC substrate	5H – 7H
PMMA substrate	6H – 8H
Adhesion to film	Excellent
Steel Wool resistance	Excellent

To achieve the optimum hardness, a dilution of 40-50% of solid and a UV dose of >500 mJ/cm² are required.

***Minimum intensity recommended for Spot lamp system: 300 mW/cm²

***Minimum intensity recommended for Flood lamp system: 125 WPI or 49 Wp/cm

SAFETY AND HANDLING

The un-cured adhesive can be cleaned from apparatus with isopropyl alcohol (IPA), MIBK, methyl ethyl ketone (MEK), or commercial alcohol based cleaning solution.

Use caution in handling this material. Avoid direct skin and eye contact. Use only in well ventilated areas. Use protective clothing, gloves and safety goggles. Read [Material Safety Data Sheet](#) before handling.

The information presented here represents our best available information and is believed to be reliable, but it does not constitute any guarantee or warranty. Inasmuch as Addison Clear Wave has no control over the exact manner in which others may use this information, it does not guarantee the results to be obtained. Nor does the company make any expressed or implied warranty of merchantability, or fitness for a particular purpose concerning the effects or results of such use. Purchasers are further responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the production processes and applications so as to ensure safety, quality and effectiveness. Addison Clear Wave makes no warranties and assumes no liability in connection with the use or inability to use this product.