




L2002-C56

UV-Curable Optical Resin for Nano Imprint Lithography



PRODUCT DESCRIPTION:

- Base chemistry: acrylate, radical polymerization
- One component resin ready for use, solvent-free, UV curing


PRODUCT USE:

- Nano imprint Lithography
- Lens and prism bonding
- LiDAR lens

FEATURES:


- High Tg, robust reliability performances, high heat resistance, good flow properties, excellent adhesion, high hardness, and spin coat-able
- Suitable for solder reflow post process

OPTICAL DATA:



Refractive index of cured film (25 °C)
 @ 589.3 nm (D): 1.511
 @ 486.1 nm (F): 1.518
 @ 656.3 nm (C): 1.508

L2002-C42 Refractive Index at 25 °C



Abbe Number at 25 °C (V_d): 51.5

GENERAL USAGE INFORMATION:

- Shipment:** no restriction on shipment
- Storage:** After receipt in black syringes or amber HDPE bottles, room temperature storage (15-30°C) in the original container is required.
- Shelf life (20 - 25°C):** 6 months
- Pot life or working life (20 - 25°C):** 3 months

UV CURING CONDITIONS: L2002-C56 is required to cure in between two substrates, in nitrogen or in the absence of air.

UV curing conditions for film thickness of 5 to 125 micron

- UV curing conditions: UV dose (mJ/cm² in nitrogen) >1,000
- Light sources:
 - * Metal halide/Mercury UV: UV-A (320-400 nm), intensity: 100-1,000 mW/cm²
 - * or LED-365 nm, UV light intensity: 100 to 1,000 mW/cm²

LED-365 nm		Metal Halide/Mercury(UV-A: 320-400 nm)	
UV intensity(mW/cm ²)	time (sec)	UV intensity(mW/cm ²)	time (sec)
100	10 to 20 sec	100	10 to 20 sec
or 200	5 to 10 sec	or 200	5 to 10 sec
or 300	4 to 6 sec	or 300	4 to 6 sec
or 400	3 to 5 sec	or 400	3 to 5 sec
or 500	2 to 4 sec	or 500	2 to 4 sec
or 1,000	1 to 3 sec	or 1,000	1 to 3 sec

Application notes for curing at thick film: 0.75 to 1.2 mm

It is possible to cure L2002-C56 at thick section with UV dose of ≥ 30 J/cm²

- UV Metal Halide or Mercury UV light source with UV-A (320-400 nm) with UV light intensity: 250 to 1,000 mW/cm²
- LED-365 nm with UV light intensity: 250 to 1,000 mW/cm²

LED-365 nm		Metal Halide/Mercury(UV-A: 320-400 nm)	
UV intensity(mW/cm ²)	time (sec)	UV intensity(mW/cm ²)	time (sec)
275	120 sec or more	275	120 sec or more
or 500	60 sec or more	or 500	60 sec or more
or 1,000	30 sec or more	or 1,000	30 sec or more

TYPICAL PROPERTIES

Uncured resin

Viscosity at 25 °C, mPa.s or cps: 1,100 to 1,300
 Density (g/mL): 1.2

Cured film

Appearance of cured adhesive: optically clear
 Shrinkage (volume, %): 3
 Hardness – Shore D: 90
 Glass transition temperature (DMA, °C): 145

Coefficient of thermal expansion (ASTM E831)

below Tg ($\times 10^{-6}$), °C⁻¹: 59
 above Tg ($\times 10^{-6}$), °C⁻¹: 141

Physical properties tested at 25°C, 50% RH (ASTM D638, and ASTM D790)

Tensile strength, MPa: 63
 Elongation (%): 6
 Young's Modulus, MPa: 2,900
 Operating temperature, °C: -40 to 150

SAFETY AND HANDLING

The uncured adhesive can be cleaned with isopropyl alcohol (IPA), methyl ethyl ketone (MEK), acetone, or xylene. Avoid direct skin and eye contact. Use only in well ventilated areas. Use protective clothing, gloves and safety goggles. Read Safety Data Sheet before handling. TDS updated 09092021 V4

The information presented here represents our best available information and is believed to be reliable, but it does not constitute any guarantee or warranty. Inasmuch as Addison Clear Wave has no control over the exact manner in which others may use this information, it does not guarantee the results to be obtained. Nor does the company make any expressed or implied warranty of merchantability, or fitness for a particular purpose concerning the effects or results of such use. Purchasers are further responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the production processes and applications so as to ensure safety, quality and effectiveness. Addison Clear Wave makes no warranties and assumes no liability in connection with the use or inability to use this product.