



HC-5619

Optically Clear UV-curable Hard Coat

PRODUCT DESCRIPTION:

- Base chemistry: acrylate, radical polymerization
- UV-curing

PRODUCT USE:

- Hard coating
- Protective coating
- Binder resin for nano particle coating

FEATURES:

- High Tg,
- Fast UV-curable
- High Hardness

PROPERTIES OF CURED HC-5619 ON PET:

Process	
Solid content (%)	30
Solvent use and %	MIBK, 70%
Viscosity of 30% solution (cps, 25 °C)	6
Film Properties	
% Transmission	93
% Haze	0.1
Pencil Hardness on PET	4H-5H
5H pencil with eight	600 gram
Adhesion	100/100
%T after steel wool (SW) test SW conditions: 100 g/cm ² /100 time	92
Delta Haze after SW	0.1
Surface energy mN/m ²	23
Solvent Resistance Properties	
Ethanol soak, 24 hrs (adhesion, appearance)	100/100*, O**
IPA soak, 24 hrs (adhesion, appearance)	100/100, O
Ethanol at 60°C soak, 24 hrs (adhesion, appearance)	100/100, O
Adhesion after moisture (40°C, 95% RH, 24 hrs)	100/100, O
QUV (72 hrs), yellow check	O
QUV+ ethanol soak x 72 hrs, adhesion check	100/100.O

*100/100= no delamination of the x-hatch test

**O= no delamination, no haze, no pocket and is excellent appearance

GENERAL USAGE INFORMATION:

Shipment: no restriction on shipment

Storage: After receipt in black syringes or amber HDPE bottles, room temperature storage (15-30°C) in the original container is required.

SAFETY AND HANDLING

The uncured adhesive can be cleaned with isopropyl alcohol (IPA), methyl ethyl ketone (MEK), acetone, or xylene. Avoid direct skin and eye contact. Use only in well ventilated areas. Use protective clothing, **gloves and safety goggles**. Read [Safety Data Sheet](#) before handling.

TYPICAL PROPERTIES of NEAT RESIN

Liquid

Viscosity (cps, 25 °C)	5,000 to 6,500
Storage (°C)	20 - 25
Shelf life (15 - 25 °C)	6 months
Pot life (15 - 25 °C)	3 months

Cured film

Shrinkage (volume, %)	6
Hardness – Shore D	95
Glass transition temperature (DMA, °C)	115
Refractive index of cured film (25°C) @ 589 nm	1.51
Coefficient of thermal expansion, 75 µm film below Tg (x10 ⁻⁶), °C ⁻¹	59
above Tg (x10 ⁻⁶), °C ⁻¹	113

Physical properties tested at 25°C, 50% RH (ASTM D638)

Tensile strength, MPa	20
Elongation (%)	5
Modulus, MPa	1,500

TYPICAL PROPERTIES of COATED FILM

Viscosity (cps, 25 °C in 50% PM) 6-8
 Suggested solvent: n-Butyl Acetate, propylene glycol monomethyl ether (PM or PGME), Methyl Isobutyl Ketone (MIBK), Methyl Ethyl Ketone (MEK), , IPA, Ethyl Acetate or mixture of solvents

Suggested hard coat solution for process: **25 – 50 wt %** of neat HC-5619 in n-Butyl Acetate or propylene glycol monomethyl ether (PM or PGME)

Process

Film: Plastic films (treated plastic film will enhance adhesion)
 Coating: Wire bar, roller coat, knife coat, dip coat, spin coat or spray
 Pre-curing: 60 – 80 °C for 1 – 2 min, IR heating is acceptable
 UV-curing: High, medium pressure Mercury lamp or Fusion lamp
 UV dose: **400 – 600 mJ/cm²**

Properties of coated film (3-5 µm)

Pencil Hardness

TAC film (10-15 µm)	3H
PET film	3H
PC substrate	4H
PMMA substrate	4H
Adhesion to film	Excellent
Steel Wool resistance	Excellent

To achieve the optimum hardness, a dilution of 40-50% of solid and a UV dose of >500 mJ/cm² are required.

The information presented here represents our best available information and is believed to be reliable, but it and does not constitute any guarantee or warranty. Inasmuch as Addison Clear Wave has no control over the exact manner in which others may use this information, it does not guarantee the results to be obtained. Nor does the company make any expressed or implied warranty of merchantability, or fitness for a particular purpose concerning the effects or results of such use. Purchasers are further responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the production processes and applications so as to ensure safety, quality and effectiveness. Addison Clear Wave makes no warranties and assumes no liability in connection with the use or inability to use this product. 102019